

# TIMBEREX

WOOD FINISHING OIL



## TIMBEREX® THIXO

### Transparent thixotropic wood stain

- Transparent and light-stable
- Thixotropic alkyd resins
- Penetrates for deep protection
- Non film forming
- Enhances the wood structure



# TIMBEREX® THIXO

## DESCRIPTION

Slight thixotropic solvent based wood stain based on special urethane modified linseed oil alkyd resins. TIMBEREX® Thixo is an easy to apply thixotropic stain with great protective and cosmetic qualities with a slightly thicker texture than other wood-stains. This allows for a thicker coating of the product to be applied for better long-term protection and makes it more convenient to use, especially for overhead work. Transparent and colour fast - accentuates wood grains - very penetrating product - penetrative treatment and protection - excellent UV-rays and weather resistance – micro porous, so no risk of blisters or peeling off - easier maintenance - not a film former.

## RECOMMENDED USE

Protective and decorative impregnation of interior and exterior woodwork. Remark: colourless TIMBEREX Thixo is only suitable for internal use.

## RECOMMENDED SYSTEM

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit or similar.

Old stripped paint: rub down up to the bare non-impregnated wood and remove all dust before application.

Maintenance: clean substrate with white spirit and apply 2 or 3 thin coats of TIMBEREX Thixo.

## TECHNICAL DATA

Density (g/cm³):	0.86 - 0.89
Gloss Level:	Semi-Matt
Solids Content in weight:	37 - 40%
Solids content in volume:	30 - 33%

## DRY TIMES BY 20° C/RH 50%

Touch dry:	3 hours
Dry to handle:	3 hours
Dry to recoat:	24 hours

## RECOMMENDED WET FILM THICKNESS

100 micron (cons.: 10 m²/l)

## RECOMMENDED DRY FILM THICKNESS

32 micron (cons.: 10 m²/l)

## THEORETICAL CONSUMPTION

10 m²/l

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

Apply in a dry and well-ventilated area.

## APPLICATION & THINNING: BRUSH

By preference, apply undiluted.

## APPLICATION & THINNING: ROLLER

By preference, apply undiluted.

## APPLICATION & THINNING: AIRLESS SPRAY

By preference, apply undiluted. Nozzle: 09 - 013 / Pressure: 150 bars

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

By preference, apply undiluted.

## CLEANING OF EQUIPMENT / SPILLS

White spirit or similar

## REMARKS

Incorrect use of TIMBEREX Thixo means that it can still be fully or partly removed with White Spirit within the first few days after application.

## SAFETY DATA

VOC level:	max. 550 g/l
VOC readymix:	max. 550 g/l
VOC category:	IIA/f
VOC limit:	700g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety. Information printed on the can.

## SHELF LIFE

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Date issued: 24/03/2025

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)