TIMBEREX
WOOD FINISHING OIL

TIMBEREX® THIXO

Transparent thixotropic wood stain

- Transparent and light-stable
- Thixotropic alkyd resins
- Penetrates for deep protection
- Non film forming
- Enhances the wood structure

TIMBEREX® THIXO

DESCRIPTION
Slight thixotropic solvent based wood stain based on special urethane modified linseed oil alkyd resins. TIMBEREX® Thixo is an easy to apply thixotropic stain with great protective and cosmetic qualities with a slightly thicker texture than other wood-stains. This allows for a thicker coating of the product to be applied for better long-term protection and makes it more convenient to use, especially for overhead work. Transparent and colour fast - accentuates wood grains - very penetrating product - penetrative treatment and protection - excellent UV-rays and weather resistance – micro porous, so no risk of blisters or peeling off - easier maintenance - not a film former.

ODPORÚČANÉ POUŽITIE
Protective and decorative impregnation of interior and exterior woodwork. Remark: colourless TIMBEREX Thixo is only suitable for internal use.

ODPORÚČANÝ SYSTÉM
New wood: rub down and make it dust free. Tropical wood is degreased with white spirit or similar.
Old stripped paint: rub down up to the bare non-impregnated wood and remove all dust before application.
Maintenance: clean substrate with white spirit and apply 2 or 3 thin coats of TIMBEREX Thixo.

TECHNICAL_DATA

Hustota (g/cm³):	0.86 - 0.89
Úroveň lesku:	Semi-Matt
Obsah pevných látok v hmotnosti:	37 - 40%
Obsah pevných látok v objeme:	30 - 33%

DRY TIMES BY 20º C/RH 50%

Na dotyk suché:	3 hours
Suché na manipuláciu:	3 hours
Suchý na opätovné natieranie:	24 hours

ODPORÚČANÁ HRÚBKA MOKRÉHO FILMU
100 micron (cons.: 10 m²/l)

ODPORÚČANÁ HRÚBKA SUCHÉHO FILMU
32 micron (cons.: 10 m²/l)

TEORETICKÁ SPOTREBA
10 m²/l

PRAKTICKÁ VÝDATNOSŤ
Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

NÁVOD NA POUŽITIE
To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE
Apply in a dry and well-ventilated area.

APLIKÁCIA A RIEDENIE: ŠTETEC
By preference, apply undiluted.

APLIKÁCIA A RIEDENIE: VALEC
By preference, apply undiluted.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE
By preference, apply undiluted. Nozzle: 09 - 013 / Pressure: 150 bars

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ
By preference, apply undiluted.

ČISTENIE ZARIADENIA / POSTRIEKANIE
White spirit or similar

POZNÁMKY
Incorrect use of TIMBEREX Thixo means that it can still be fully or partly removed with White Spirit within the first few days after application.

SAFETY DATA

Úroveň VOC:	max. 550 g/l
VOC readymix:	max. 550 g/l
Kategória VOC:	IIA/f
Limit VOC:	700g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety. Information printed on the can.

SKLADOVATEĽNOSŤ
Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last_updated: 22/06/2026

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu